

## WATERPROOFING FLEXIBLE POLYMERIC BALDRAN PLUS® 5000

### PRODUCT

**BALDRAN PLUS® 5000** is a bicomponent waterproofing system having an acrylic-based emulsion, cement and special additives which when mixed form a flexible polymeric mortar which is waterproof and has excellent adhesion to the substrate. The product offers high performance to seal a positive hydrostatic pressure.

The product is non-toxic and does not alter the potability of water.

### SEGMENTS OF USE

Waterproofing of water towers and potable water reservoirs among others.

### PREPARATION OF THE SURFACE

The surface should be clean and free of imperfections.

The cleaning can be executed with a high-pressure hose or brush with hard bristles.

In case of fissures up to 0.3 mm, we recommend the application of the product **Reisflex PU** for correction before the waterproofing. In some cases a bridge of adherence has to be created. Sharp edges must be rounded.

### PREPARATION OF THE PRODUCT

Mix component B (powder) with component A (liquid) in an adequate container mechanically for 3 minutes or manually for 5 minutes until it results in a homogeneous compound free of lumps. In large quantities, use concrete mixer. Once the components are mixed the mixture must be used within 40 minutes. **DO NOT MIX WITH WATER.**

### APPLICATION OF THE PRODUCT

Before beginning the application, moisten the surface with water avoiding puddles. **BALDRAN PLUS® 5000** should be applied with brushes or brooms spreading the product constantly. The product should be applied on uniform layers at right angles.

After applying the first layer, wait from 4 to 8 hours for the second layer. Between the 2nd and 3rd layers, reinforce with a 2x2 mm polyester mesh. Wait 5 days to test for leaks.

If **BALDRAN PLUS® 5000** is used on horizontal surfaces, then a minimum 3 cm layer of concrete as mechanical protection must be applied over: batch base, cement + sand = 1/3.

### RECOMMENDATIONS

- Decontrol the area after 3 days
- For open areas or areas under the sun, hydrate for a minimum of 3 consecutive days
- After the cure, test for water-tightness with water for a minimum period of 72 hours
- Clean the tools with water

### Negative Waterproofing

In case of negative pressure, you should apply **BALDRAN PLUS® 1000** and after the cure, apply **BALDRAN PLUS® 5000**.

### BENEFITS

- Avoids the formation of mold and moisture
- Easy application
- Resistant to water pressure
- Excellent adherence without necessity of roughcast
- Excellent barrier against sulfates and chlorates

### TECHNICAL CHARACTERISTICS

Baldran Plus® 5000 Part A	Baldran Plus 1000 Part B
Form: viscous liquid	Aspect: powder
Color: white	Color: gray
Density: at 25C (77F): 1 to 1.07	
pH: 7 to 9	
Brookfield Viscosity: 100 to 400 Cps	Package: 7 kg and 14 kg
Package: 5 kg	
Time of application: 40 minutes	
Temperature of application: 5C to 35C (41F to 95F)	
Package: 18 kg	

### YIELD

**Baldran Plus:** 3 kg/m<sup>2</sup>

The yield can be altered depending on the hydrostatic pressure (positive or negative); in this case consult our technical department.

### CLEANLINESS AND SAFETY

Use protective glasses and rubber gloves. Direct contact with the skin should be avoided (can cause irritation). In case of contact with the skin or eyes, wash immediately with abundant water and consult a doctor. Keep out of the reach of children and animals.

### STORAGE

**BALDRAN PLUS® 5000** should be stored in a dry and ventilated location at a temperature below 77F (25C).

**Validity:** 12 months

#### Reis e Reis Indústria e Comércio Ltda

Rua Wilton Reis Costa, 220 - Cond.Ind. Eldorado

São José dos Campos / SP CEP 12238-574

Fone/Fax: (12) 3966-9977

e-mail: [vendas@reisereis.com.br](mailto:vendas@reisereis.com.br)

Home-page: [www.reisereis.com.br](http://www.reisereis.com.br)

*Our technical advice concerning the application of the product is made verbally, in writing and through demonstration depending on the interest of the customer.*

*It should be noted that the application of the product is a precision process and when it is not applied by Reis e Reis, the company disclaims any responsibility; therefore, the responsibility is that of the customer. Regarding the storage and use of the product, any resulting change in its properties will be the complete responsibility of the customer.*

*The liability of Reis e Reis will be limited to any damage or loss in value of the goods supplied by the company and used by the customer. We guarantee the unquestionable quality of our products in accordance with our terms of sale and supply.*