

Epoxy Primer

RR PRIMER®

PRODUCT

RR Primer is an adhesion promoter between concrete and epoxy coatings, aims to ensure adherence avoiding delamination of materials.

PREPARATION OF APPLICATION

Preparation: Because it is a bi-component, components **A + B** must be mixed using a mechanical mixer at low speed.

The concrete substrate must be fully cured and dry, free from dust, oil, grease and other products that have mold release characteristics.

APPLICATION

Apply with roller of thin wool in a single coat. The finishing material should be applied within 10 to 12 hours.

TOOL CLEANING

Clean tools with solvents such as ethyl alcohol, acetone or thinner.

CHARACTERISTICS AND PERFORMANCE

| PROPERTIES | Part A | Part B | Mixture |
|--|-----------|-----------|------------|
| Color | Colorless | Nut-brown | Caramel |
| Relation to mixture | 100 | 50 | 100:50 |
| Dry to touch 77°F (25°C) | | | 2h |
| Time to cure 77°F (25°C) (75 micron layer) | | | 7 days |
| Time to use 77°F (25°C) (100g) | | | 40 minutes |
| Packaging | | | Kit.3,3 Kg |

PROPIEDADES FÍSICAS

| CHARACTERISTICS | CHARACTERISTICS |
|-------------------|------------------------|
| Specific Weight | 1~15 g/cm ³ |
| Theoretical Yield | 0,25 Kg/m ² |

YIELD

Can vary depending on temperature and porosity of the concrete.

CLEANLINESS AND SAFETY

Users should use protective glasses and rubber gloves. Direct contact with the skin should be avoided (can cause irritation). In case of contact with skin or eyes, wash immediately and abundantly with water, consult a doctor and inform the type of product.

Keep packages out of the reach of children, animals and sources of heat.

STORAGE

Should be stored in a dry, ventilated place and at a temperature of 70°F – 73°F (21°C – 23°C).

VALIDITY

9 months in sealed package.