

Sealant and Polyurethane

REISFLEX® PU-50

PRODUTO

ReisFlex® PU-50 is a monocomponent polyurethane adhesive sealant with ultraviolet (UV) protection. It is developed to seal various construction / fabrication details that are subject to movements that require greater flexibility. It looks like a tough, flexible rubber.

SEGMENTS OF USE

ReisFlex® PU-50 is designed to seal control, expansion or caulk joints, such as:

- Automotive naval;
- Automotive industry;
- Aerospace industry;
- Civil construction

APPLICATION

For good adhesion and satisfactory results, the surface to be applied **ReisFlex® PU-50** must be clean, free from dust, contaminants and dirt (grease, oil, silicones). **ReisFlex® PU-50** accepts painting after its full cure.

Application Limitations: Should not be applied on frozen or water surfaces, it should not be applied over silicones.

Note: At the time of application, prevent the packaging in use, being exposed to the sun or temperatures above 25 ° C, there may be a change in viscosity and product performance.

SPECIFICATION

ReisFlex® PU-50 meets and exceeds the performance requirements of: ASTM C920 Types, Grade NS Class 25 Fed. Spec. TT-S-00230 C type II Class A (Flexibility and 50% accommodation at joints) AAMA 808.3-92 (Composite Sealant for Exterior Perimeter).

CHARACTERISTICS AND PERFORMANCE

Chemical Composition	Polyurethane
Physical State	Pasty Tixotropic
Packaging	Cartridge 310 mL and Sachets 400 mL and 600 mL
Colors	Gray, White, Black and Colors.
Yield (1 cartridge 310 mL)	3 linear meters in joint of 1cmx1cm
Resistance	Water, Gasoline and Diesel.

PHYSICAL PROPERTIES AND METHODOLOGY OF TESTS

CHARACTERISTICS	RESULTS	METODOLOGY OF TESTS
Solids content	Min. 97%	-
Density	1,23g/cm ³ +/- 0,02	DIN 53505
Tensile strength	8,5 Mpa (N/mm ²) 1,240	DIN 53504
Stretch	450%	DIN 53505
Thixotropic	Positive	TS-S 0023C (COM-NBS)
Hardness (Shore A)	50 ± 5	DIN 53505
Working Temperature	-5°C to 45°C	TS-S 0023C (COM-NBS)
Touch Dry	45 minutes to 1 Hour	
Total Cure	3 mm every 24 hours with 50% relative humidity	

ORGANIC VOLATILE COMPOUNDS

V.O.C.	CONTAINS
Cartridge 310 mL	0,293 g/L
Sachet 600 mL	0,586 g/L

HYGIENE AND SAFETY

In contact with skin or eyes, rinse with plenty of water for at least 15 minutes. If swallowed, induce vomiting, drink water and seek medical advice. Keep out of reach of children and animals.

VALIDITY AND STORAGE

12 months, provided it is stored in a dry and ventilated place at a temperature below 25°C.